



Epoxy Anti-Static Coating

永保新無溶劑抗靜電面漆



Product No. : #1015AS

產品編號 : #1015AS

General Description :

A two-pack finish coating based on special solvent-less Epoxy Resin and Hardener with conductive pigments.

一般說明:

由特殊無溶劑環氧樹脂(Epoxy Resin)及硬化劑配以導電性顏料精製而成之二液型無溶劑面漆。

Uses :

For floor of electronics factories, wafer fab houses, clean rooms, laboratories, hospitals, precision equipment rooms, computer rooms, powder factories, knitting factories, solvent stores, military stores, etc.

用途:

電子廠, 晶圓加工廠, 無塵室, 實驗室, 醫院, 精密儀器室, 電腦房, 粉體工廠, 紡織廠, 溶劑儲存場, 軍火彈藥庫房等地面之水性導電底漆。

Characteristics :

1. Tough and hard film with very good adhesion.
2. Excellent resistance to oil and water.
3. High build coating without pinhole, 200 μ pre coat.
4. Excellent resistance to many chemicals and corrosion.
5. System resistance value $10^4 \sim 10^6$ ohms, can promptly eliminate generated static charges.

特點:

1. 漆膜堅韌, 附著力非常優良。
2. 耐水及耐油性特優。
3. 刷塗一道即可得200 μ m以上無針孔厚漆膜。
4. 耐藥品及防蝕等性能非常優良。
5. 系統電阻值 $10^4 \sim 10^6$ ohms, 能迅速將生的靜電導除。

Color-Availability :

Limited

可調配顏色:

有限制(請參考色卡)

Technical Data :**技術資料:**

Finish 光澤		Gloss, Above 85% 有光, 85% 以上
Weight 重量		Above 1.2 Kg/ L (mixture) 1.2 公斤/公升以上 (混合漆)
Viscosity (25 °C) 黏度 (25 °C)		110 ~ 140 KU (mixture) 110 ~ 140 KU (混合漆)
Drying Time (25 °C) 乾燥時間 (25 °C)	Set-to-touch 指觸	within 6 hrs 6 小時以內
	Dry hard 堅膜	within 18 hrs 18 小時以內
	Fully cured 完全硬化	7 days 7 天
Optimum Film Thickness 漆膜厚度	Wet 濕膜	1025 microns 1025 (微米)
	Dry 乾膜	1000 microns 1000 (微米)
Overcoating Intervals (25 °C) 塗料間隔 (25 °C)	Min. 最少	24 hrs. 24 小時
	Max. 最多	2 days 2 天
Pot Life (25 °C) 可用時間 (25 °C)		within 1/2 hr. (mixture) 1/2 小時以內 (混合漆)
Theoretical Coverage 理論塗佈量		1.4 Kg/m ² (1000 μ) 1.4 公斤/平方米 (1000 μ) 2.5 Kg/m ² (1800 μ) 2.5 公斤/平方米 (1800 μ)
Solid by Volume 固體容積		95% above (mixture) 95%以上, (混合漆)
Mixer Rate 混合比		Base : Hardener = 4 : 1 (Weight Rate) 主劑:硬化劑 = 4:1 (重量比)
Stock Shelf Life 貯藏安定性		Minimum 1 year under normal storage conditions. 正常情況下, 至少1年

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk



No.1015AS

虹牌 油漆



ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Component(s) : Two
Dilution : No.1005 Epoxy Thinner
(only for cleaning tools)
Application Method : Trowel and Brush.

使用說明:

組合成份數目 : 2
稀釋 : No. 1005 永保新調薄劑
(僅可用以清洗工具)
塗裝方法 : 鏟填, 刷塗

Packing Style :

1015AS Epoxy Anti-static Coating
4.54 Kg / USG / Can
22.7 Kg / 5 USG / DR

包裝:

1015AS 永保新無溶劑抗靜電漆:
4.54 公斤/美卡/罐
22.7 公斤/5美卡/桶



Material Handling :

1. Mix base, hardener according to mixing ratio and stir thoroughly.
2. Adhered moisture, grease, dirt, rust and corrosive salts on substrate must be cleaned thoroughly.
3. Avoid applying the paint in rainy weather or humidity above 85% RH, particularly, a wet surface must be thoroughly dried.
4. All equipments must be cleaned immediately after used.
5. Start applies after the surface of concrete wall or concrete products dry thoroughly.
6. When overcoating interval is exceeded, paint surface must be roughened to insure adhesion.

注意事項:

1. 主劑與硬化劑必須按規定比例均勻調合後再使用。
2. 被塗表面之水份, 油脂, 污泥及灰塵等附著污物必須清除乾淨。
3. 陰雨或大氣相對濕度在85% RH以上時, 應避免施工, 尤以表面潮濕時, 必須使之完全乾燥。
4. 塗裝器具使用完, 應立即洗淨。
5. 直接塗於水泥牆或水泥製品表面時, 必須等完全乾燥後, 才可施工。
6. 塗裝間隔超過規定時間, 則須將漆面磨粗以增加其附著力。



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk

