



Epoxy Alloy Primer

永保新合金用底漆



ISO 9001:2000
Cert. No. 01 100 6507

Product No. : EP-1020

產品編號 : EP-1020

General Description :

A two-pack, special alloy primer based on epoxy resin hardener and special pigments.

一般說明 :

由環氧樹脂(Epoxy Resin) 及硬化劑, 配以特殊顏料精製而成之二液型合金用防銹底漆.

Uses :

Used for galvanized steel, aluminum, alum-alloy metal and stainless after cleaning.

用途 :

經清潔處理後之鍍鋅, 鋁板, 不銹鋼等材質用防銹防蝕底漆.

Characteristics :

1. Tough and hard film with very good adhesion.
2. Excellent resistance to sea water and rust preventive properties.
3. Excellent resistance to mechanical damage.
4. Very good adhesion to any topcoat of coating.
5. Very good resistance to oil and splash of mild chemical.

特點 :

1. 漆膜堅韌, 附著力強.
2. 耐海水與耐水性及防蝕性能特佳.
3. 耐磨損性極優.
4. 對任何上層漆均有良好附著性.
5. 耐油性及耐多種藥品性極優.

Color-Availability :

Green

可調配顏色 :

綠色

Technical Data :**技術資料 :**

Finish 光澤		Flat 平光
Flash Point 閃火點		Above 20°C (68°F) 20°C (68°F) 以上
Weight 重量		1.3Kg/L (Mixture) 1.3公斤/公升 (混合漆)
Viscosity (25 °C) 黏度(25 °C)		70 ~ 85 KU 70 ~ 85 KU
Drying Time (25 °C) 乾燥時間 (25 °C)	Set-to-touch 指觸	1/2 hr 1/2 小時
	Dry hard 堅膜	6 hrs 6 小時
	Full cured 完全硬化	7 days 7 天
Optimum Film Thickness 漆膜厚度	Wet 濕膜	96 microns 96 微米
	Dry 乾膜	50 microns 50 微米
Overcoating Intervals (25 °C) 塗料間隔 (25 °C)	Min. 最少	8 hrs 8 小時
Temperature Resistance 耐熱溫度		Around 100°C 約100°C
Theoretical Coverage 理論塗佈量		10.4 m ² /L, 8 m ² /Kg. 10.4 平方米/公升, 8 平方米/公斤.
Solid by Volume 固體容積		52% 52%
Stock Shelf Life 貯藏安定性		Minimum 1 year under normal storage conditions. 正常情況下, 至少1年.

**TAI HING HONG 大興行**

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515



紅牌油漆

Material Handling :

1. Ensure adequate ventilation during application.
2. For spray application the necessary health precautions must be observed.
3. Keep away from heat sources.
4. Moisture, grease, sludge, old paint and rust must be thoroughly removed from substrate.
5. Mix base and hardener according to the mixing ratio and stir thoroughly, than setting 10~20 mins.
6. Avoid applying the paint in rainy or humid weather, particularly, a wet surface must be thoroughly dried.
7. All equipments must be cleaned immediately after use.
8. When used inside tanks, sufficient ventilation must be provided.
9. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

注意事項:

1. 在施工時保證足夠空氣流通。
2. 噴塗施工時,必須注意一切安全措施。
3. 遠離熱源
4. 被塗物表面水份,油脂,污泥,灰塵,鐵鏽及腐蝕性鹽類等附著物必須清除乾淨。
5. 主劑及硬化劑,必須按規定比例,均勻調合,放置 10~20 分鐘再使用。
6. 陰雨或大氣相對濕度在 85% RH 以上時,應避免施工,以表面潮濕者,必須使之完全乾燥。
7. 各項工具於使用完畢,須立刻洗淨。
8. 於貯槽內施工時,須注意予以充分通風。
9. 如稀釋劑非由我們推薦的,我們將不會保證任何有關使用上所引致的後果及缺點。



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515

