



Water-based Flooring Epoxy Topcoat

水性環氧樹脂地台面漆



Product No. : #1032

產品編號 : #1032

General Description :

A two-pack, water-base flooring epoxy finish coating based on Epoxy Resin.

一般說明:

由水性環氧樹脂構成之二液型地台面漆。

Uses :

Used as decorative topcoat, and protection of interior or exterior flooring cement surface for office buildings, hospitals, hotels, food factory and public places.

用途:

辦公大樓, 觀光飯店, 公共場所, 食品工廠, 醫院, 店舖, 住宅等水泥構造地台用之防護, 裝飾用面漆

Characteristics :

1. Excellent hardness, adhesion and abrasion resistance.
2. Excellent resistance to oils, acids alkalis solvents and corrosive salt.
3. Excellent resistance contamination resistance.
4. Excellent resistance to weathering with gloss retention.
5. With dust proofing property
6. Diluted with water; environmental friendly; no danger of fire and toxicity.

特點:

1. 具有優良之附著性, 硬度及耐磨性
2. 耐藥品性非常優良, 不易受酸, 鹼, 油脂, 溶劑及鹽類等腐蝕性物質侵蝕
3. 耐污染性極優.
4. 耐油性及耐多種藥品性極優.
5. 防塵性優良.
6. 使用清水為溶劑, 無公害及引火危險

Color-Availability :

White and Different Colors

可調配顏色:

白色及各色

Technical Data :**技術資料:**

Finish

光澤

Weight

重量

Viscosity (25 °C)

黏度 (25 °C)

Drying Time (25 °C, RH=60%)

乾燥時間 (25 °C, RH=60%)

Optimum Film Thickness

漆膜厚度

Overcoating Intervals (25 °C)

塗料間隔 (25 °C)

Theoretical Coverage

理論塗佈量

Solid by Volume

固體容積

Stock Shelf Life

貯藏安定性

Set-to-touch

指觸

Dry hard

堅膜

Fully cured

完全硬化

Wet

濕膜

Dry

乾膜

Min.

最少

Max.

最多

Gloss, Above 60%

有光 60% 以上

1.05 Kg/ L (mixture)

1.05 公斤/公升 (混合物)

75 ~ 90 KU

75 ~ 90 KU

4 hrs

4 小時

12 hrs

12 小時

7 days

7 天

100 microns

100 微米

40 microns

40 微米

18 hrs

18 小時

10.0 m²/L,

10.0 平方米/公升

45%

45%

Minimum 1 year under normal storage conditions.

正常情況下, 至少1年



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk





ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Component(s) : Two
No. of Coat(s) : One~Two
Dilution : 0~5% with tap water
Preceding Coats
Cement : 1030CP Water-base Epoxy Clear
Primer/Sealer
Steel : 1035 Water-base Epoxy Aluminum
Tripolyphosphate Primer

使用說明:

組合成份數目 : 2
塗施層面 : 1~2
稀釋 : 0~5% 自來水
適用底漆
水泥底材 1030CP 水性環氧樹脂透明底漆
鋼材 1035 水性環氧三聚磷酸鋁
防銹底漆

Packing Style :

1032 Water-Based Flooring Epoxy
Topcoat 4 Kg/ USG /Can
20 Kg/ 5USG/ DR

包裝:

1032 水性環氧樹脂: 4 公斤/ 美卡/ 罐
地台面漆 20 公斤/ 5美卡/ 桶

Material Handling :

1. For spray application the necessary health precautions must be observed.
2. The moisture, grease, dirt, dust and other contaminants on applied surface must be cleaned thoroughly.
3. Mix base and hardener according to the mixing ratio and stir thoroughly.
4. Avoid applying the paint in rainy or humid weather, particularly, a wet surface must be thoroughly dried.
5. All equipments must be cleaned immediately after use.
6. When used inside tanks, sufficient ventilation must be provided.
7. Since without the stable glue time, so please follow the pot life when applying

注意事項:

1. 噴塗施工時, 必須注意一切安全措施.
2. 被塗物表面之油脂, 灰塵, 水份及其他附著物, 必須清除乾淨才能施工
3. 主劑及硬化劑, 必須按規定比例, 均勻調合.
4. 陰雨或潮濕時, 儘量避免施工, 尤以表面潮濕者, 必須使之完全乾燥.
5. 各項工具於使用完畢, 須立刻洗淨.
6. 於貯槽內施工時, 須注意予以充份通風.
7. 本產品無明顯的膠化時間, 請於規定可用時間內使用完畢.



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk

