



Epoxy Middle Coating

永保新中途漆



ISO 9001:2000
Cert. No. 01 100 6507

Product No. : EP-1060

產品編號 : EP-1060

General Description :

A two-pack, middle coating based on epoxy resin special hardener and inhibitive-rust pigments.

Uses :

Middle coating for steel-pipes, steel structures, bridges and factory equipment after applying epoxy primer or Inorganic zinc primer to avoid bubbling occurring. Also for concrete wall, concrete products,... etc. As inter-mediated coat between primer and topcoat.

Characteristics :

1. Tough and hard film with very good adhesion.
2. Good adhesion for primer and can fill the holes that caused by primer to avoid blistering occurring.
3. Good electric insulation with excellent resistance to mechanical damage.
4. Excellent resistance to oils, solvents and chemicals.

Color-Availability :

White, Gray or Brown

一般說明:

由環氧樹脂 (Epoxy Resin), 及特殊硬化劑配以特殊顏料精製而成之二液型中途底漆。

用途:

鋼管, 鋼架, 橋樑, 工廠設施等鋼鐵構造物施塗永保新底漆或無機鋅粉底漆後, 使用之防止起泡用中途底漆及水泥牆, 水泥製品用中途漆。

特點:

1. 漆膜堅韌而富可撓性及附著性。
2. 與底漆附著力強, 更可填補底漆之孔穴防止上塗面漆起泡
3. 耐磨性及電氣絕緣性非常優良。
4. 耐油耐溶劑及耐化學性極優。

可調配顏色:

白色, 灰色, 棕紅色

Technical Data :

Finish
光澤

Weight
重量

Viscosity (25 °C)
粘度(25°C)

Drying Time (25 °C)
乾燥時間 (25 °C)

Optimum Film Thickness
漆膜厚度

Overcoating Intervals (25 °C)
塗裝間隔(25 °C)

Theoretical Coverage
理論塗佈量

Solid by Volume
固體容積

Stock Shelf Life
貯藏安定性

技術資料:

Flat
平光

1.45Kg/L (Mixture)
1.45公斤/公升以上(混合漆)

70 ~ 90 KU

Set-to-touch
指觸
1-1/2 hr
1-1/2 小時

Dry hard
硬乾
6 hrs
6 小時

Full cured
完全硬化
7 days
7 天

Wet
濕膜
100 microns
100 微米


Dry
乾膜
50 microns
50 微米

Min.
最少
8 hrs
8 小時

47.3 m²/USG
47.3平方公尺 / 美卡

70%
70%

Minimum 1 year under normal storage conditions.
正常情況下,至少1年.



虹牌油漆

No.EP-1060

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515





ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Component(s)	: Two
No. of Coats	: One
Dilution	: 5~15% (by wt.) No. SP-12 Epoxy Thinner.
Subsequent Coats	: Topcoats of Epoxy, Vinyl, Chlorinated Rubber, or Polyurethane System,
Preceding Coats	: No. EP-03AA Epoxy Zinc Rich Primer Fire Cut-FM-900 Fire Resistance Coating No. IZ-01 Galvo-Zinc
Mixing Ratio	: Base : Hardener = 92.1 : 7.9 (by wt.)
Pot Life (25°C)	: 8 hrs (Mixture)
Application Method	: Airless Spray, Brush

Packing Style :

5.49 Kg /USG /Can
27.12 Kg /5USG /DR

使用說明:

組合成份數目	: 2
塗施層面	: 1
稀釋	: 5~10% (重量比) No.SP-12 永保新調薄劑.
適用面漆	: 永保新, 永美, 橡膠或優麗面漆
適用底漆	: EP-03 永保新鋅粉漆. FM-900 防火漆 IZ-01 無機鋅粉漆.
混合比	: 主劑:硬化劑=92.1 : 79 (重量比).
可用時間(25°C)	: 8小時 (混合漆)
塗裝方法	: 無氣噴塗, 刷塗, 滾塗.

包裝:

5.49 公斤/美卡/罐
27.12公斤/5美卡/桶

Material Handling :

1. Mix base and hardener according to the mixing ratio and stir thoroughly.
 2. When substrate is damp with dew or during rainy weather painting must be suspended.
 3. Moisture, grease, sludge, old paint and rust must be thoroughly removed from substrate.
 4. All equipments must be cleaned immediately after use.
 5. For spray application the necessary health precautions must be observed.
 6. Ensure adequate ventilation during application.
 7. Keep away from heat sources.
 8. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.
1. 主劑及硬化劑，必須按規定比例均勻調合。
 2. 表面潮濕，凝結有露水或在陰雨天時，應避免施工。
 3. 被塗物表面水份，油脂，污泥，灰塵，鐵銹及腐蝕性鹽類等附著物必須清除乾淨。
 4. 各項工具於使用完畢，須立刻洗淨。
 5. 噴塗施工時，必須注意一切安全措施。
 6. 在施工時保證足夠空氣流通。
 7. 遠離熱源。
 8. 如稀釋劑非由我們推薦的，我們將不會保證任何有關使用上所引至的後果及缺點。



TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515

