



Water-based Epoxy Conductive Primer

永保新導電底漆



Product No. : #1098W

產品編號 : #1098W

General Description :

A two-pack Epoxy conductive primer based on water-based Epoxy resin, hardener and special conductive filler and additives.

一般說明 :

由水性環氧樹脂,硬化劑及特殊導電填充料,漆加劑構成之二液型永保新導電底漆.

Uses :

For floor of electronics factories, wafer fab houses, clean rooms, hospitals, precision equipment rooms, computer rooms, powder factories, knitting factories, solvent stores, military stores, etc.

用途 :

電子廠,晶圓加工廠,無塵室,醫院,精密儀器室,電腦房,粉體工廠,紡織廠,溶劑儲存場,軍火彈藥庫房等地面之水性導電底漆.

Characteristics :

1. Water based, low VOC, suitable for use in interior and enclosed area application.
2. Excellent conductivity, can effectively remove static charge.

特點 :

1. 水性低VOC, 適合室內及密閉空間施工使用.
2. 導電性佳, 可有效導除靜電

Color-Availability :

Black

可調配顏色 :

黑色

Technical Data :**技術資料:**

Weight 重量		Above 1.0 Kg/ L (mixture) 1.0 公斤/公升以上 (混合漆)
Viscosity (25 °C) 黏度 (25 °C)		50 ~ 60 KU (mixture) 50 ~ 60 KU (混合漆)
Drying Time (25 °C) 乾燥時間 (25 °C)	Set-to-touch 指觸	within 6 hrs 6 小時以內
	Dry hard 堅膜	within 12 hrs 12 小時以內
	Fully cured 完全硬化	7 days 7 天
Optimum Film Thickness 漆膜厚度	Wet 濕膜	300 microns 300 (微米)
	Dry 乾膜	100 microns 100 (微米)
Overcoating Intervals (25 °C) 塗料間隔 (25 °C)	Min. 最少	14 hrs. 14 小時
	Max. 最多	----- -----
Pot Life (25 °C) 可用時間 (25 °C)		within 1 hr. (mixture) 1 小時以內 (混合漆)
Theoretical Coverage 理論塗佈量		12.6 m ² /Gal 12.6 平方米/美卡
Mixer Rate 混合比		Base : Hardener = 33.3 : 66.7 (Weight Rate) 主劑:硬化劑 = 33.3:66.7 (重量比)
Stock Shelf Life 貯藏安定性		Minimum 1 year under normal storage conditions. 正常情況下, 至少1年



虹牌®油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk





ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Component(s) : Two
Dilution : 5 ~ 10% Water
(excluded for cleaning tools)
Application Method : Brush, Spray

使用說明:

組成份數目 : 2
稀釋 : 0~5% 自來水
(不含清洗工具)
塗裝方法 : 刷塗, 噴塗

Packing Style :

1098W Water-based Epoxy Conductive Primer
3.8 Kg / USG / Can
19 Kg / 5 USG / DR

包裝:

1098W 永保新導電底漆:
3.8 公斤/美卡/罐
19 公斤/5美卡/桶



Material Handling :

1. Adhered moisture, grease, dirt, rust and corrosive salts on substrate must be cleaned thoroughly.
2. Mix base and hardener according to the mixing ratio.
3. Avoid applying the paint in rainy weather or relative humidity exceed 85% RH.
4. All equipments must be cleaned immediately after used.

注意事項:

1. 被塗表面之水份, 油脂, 污泥及灰塵等附著污物必須清除乾淨.
2. 主劑與硬化劑必須按規定比例混合後才可使用.
3. 陰雨或大氣相對濕度在85% RH以上時, 應避免施工.
4. 塗裝器具使用完, 應立即洗淨.



No.1098W

虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihingong.biz.com.hk

