



White Primer for Emulsion Paints

白色水性水泥底漆



ISO 9001:2000
Cert. No. 01 100 6507

Product No. : 410-1

產品編號 : 410-1

General Description :

The high quality emulsion paint primer based on the alkali-and water-borne pure acrylic resin, with the special pigments and additives.

一般說明 :

由水性壓克力樹脂,配合耐候顏料及添加劑精製而成之高級水性水泥漆

Uses :

Specialized primer to be used for concrete related products.

用途 :

適用於水泥製品之打底用漆

Characteristics :

1. Easy application.
2. Good adhesive properties
3. Excellent alkali-resistant property.
4. No danger of causing fire and public hazard due to the water-based of raw material.

特點 :

1. 乾燥迅速,作業性優良
2. 附着力等強
3. 耐鹼性優良,對新水泥面的鹼鹽害,具有封阻作用
4. 使用清水為溶劑,無公害及引火危險

Color-Availability :

White

可調配顏色 :

白色

Technical Data :**技術資料 :**

Finish 光澤		Semi-gloss 平光
Weight 重量		above 1.25 Kg/L 1.25公斤/公升 以上
Viscosity (25 °C) 黏度 (25 °C)		70 ~ 90KU 70 ~ 90KU
Hiding Power 遮蓋力		6 m ² /L 6 平方米/公升
Drying Time (25 °C) 乾燥時間 (25 °C)	Set-to-touch 指觸	Within 1 hr 1 小時以內
	Dry hard 硬乾	2 hrs 2 小時以內
Optimum Film Thickness 漆膜厚度	Wet 濕膜	90 microns 90 微米
	Dry 乾膜	35 microns 35 微米
Overcoating Intervals (25 °C) 塗裝間隔 (25 °C)	Min. 最少	3 hrs 3 小時
Theoretical Coverage 理論塗佈量		38.0 m ² /Gal, 11.1 m ² /L, 8.9 m ² /Kg 38.0 平方米/加侖, 11.1 平方米/公升, 8.9 平方米/公斤
Non-volatile Content 總不揮發物		Above 50% 50%以上
Storage Shelf Life 貯藏安定性		Minimum 1 year under normal storage conditions 正常情況下, 至少一年



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk





ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Components : One
No. of Coats : One
Dilution : 5 ~ 10% with tap water
Subsequent Coats : No.380, 406, 410, 436 500-1 etc.
various emulsion paints
Application Method : Spray, Brush, Roller

使用說明 :

組成份數目 : 1
塗施層面 : 1
稀釋 : 5 ~ 10% 自來水
適用面漆 : No.380, 406, 410, 436, 500-1
等各類水泥漆
塗裝方法 : 噴塗, 刷塗, 滾塗

Packing Style :

No. 410-1 White Primer for Emulsion Paints 4.73 Kg/ USG/ Can
23.65 Kg/ 5USG/ DR

包裝 :

No.410-1 白色水性水泥底漆 4.73 公斤/美卡/ 罐
23.65 公斤/5美卡/ 桶



Material Handling :

1. The moisture, grease, dirt, dust and other contaminants on applied surface must be cleaned thoroughly.
2. Before application, stir paint evenly, and when paint is too thick the tap water can be added within specified quantity.
3. Moisture and alkali will reduce film performance and adhesion, therefore, moisture content of new constructed cement walls should be under 12%. If not, the application has to wait for 2 or 3 weeks until the walls is dry completely
4. For spray application the necessary health precautions must be observed.
5. Ensure adequate ventilation during application.
6. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

注意事項 :

1. 被塗物表面之油脂, 灰塵, 水份及其他附著物, 必須清除乾淨才能施工
2. 使用前必須充分攪拌, 太稠時, 可酌加自來水調薄, 但以不超過規定量為原則
3. 新水泥牆壁因含有水份與游離鹼性物質, 必將降低漆膜性能與附性, 必須等2~3星期, 待其完全乾燥後, 水份值在12% 以下, 始可施工
4. 噴塗施工時, 必須注意一切安全措施
5. 在施工時保證足夠空氣流通
6. 如稀釋劑非由我們推薦的, 我們將不會保證任何有關使用上所引至的後果及缺點



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk

