



# Rainbow Waterbased Cement Paint

## 彩虹漆



**Product No. : 410**

**產品編號 : 410**

### General Description :

The high quality semi-gloss emulsion paint, based on the alkali and water-borne pure acrylic resin, with the special pigments and additives.

### 一般說明 :

由水性壓克力樹脂, 配合耐候顏料及添加劑精製而成之高級水性水泥漆

### Uses :

Used as decorative topcoat, and protection of interior or exterior cement surface for office buildings, schools, hospitals, hotels, residence and public places.

### 用途 :

辦公大樓, 學校, 觀光飯店, 公共場所, 醫院, 店舖, 住宅等水泥壁, 磚造物, 石膏等內外部構造物之防護, 裝飾用面漆

### Characteristics :

1. Easy application.
2. Good adhesive properties; tough film; smooth appearance.
3. Excellent weatherability; good color retention; suitable for interior and exterior surface.
4. Diluted with water; environmental friendly; no danger of fire and toxicity.
5. Excellent water and alkali-resistant properties.
6. Wash resistance test is up to 5,000 times.

### 特點 :

1. 施工容易, 噴塗, 手刷, 滾刷皆可
2. 附着力強, 塗膜堅固, 外表美觀柔和
3. 耐候性, 保色性優良, 內外部使用皆適合
4. 使用清水為溶劑, 無公害及引火危險
5. 耐水性, 耐鹼性極優良
6. 耐刷洗試驗 5,000 次以上

### Color-Availability :

Different Colors

### 可調配顏色 :

各色

**Technical Data :**

Finish

光澤

Weight

重量

Viscosity (25 °C)

黏度 (25 °C)

Drying Time (25 °C)

乾燥時間 (25 °C)

Optimum Film Thickness

漆膜厚度

Overcoating Intervals (25 °C)

塗裝間隔 (25 °C)

Theoretical Coverage

理論塗佈量

Non-volatile Content

總不揮發物

Storage Shelf Life

貯藏安定性

**技術資料 :**

Semi-gloss

半光

above 1.2 Kg/L

1.2公斤/公升 以上

80 ~ 100KU

80 ~ 100KU

Within 1 hr

1 小時以內

4 hrs

4 小時

Set-to-touch

指觸

Dry hard

硬乾

Wet

濕膜

Dry

乾膜

Min.

最少

90 microns

90 微米

35 microns

35 微米

5 hrs

5 小時

44.0 m<sup>2</sup>/Gal, 11.7 m<sup>2</sup>/L, 8.5 m<sup>2</sup>/Kg

44.0 平方米/加侖, 11.7平方米/公升,

8.5平方米/公斤

Above 45%

45%以上

Minimum 1 year under normal storage conditions

正常情況下, 至少1年



No.410  
虹牌油漆

**TAI HING HONG 大興行**

Main Office:  
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong  
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:  
Unit 1906, 19/F., Bonham Trade Centre,  
50 Bonham Strand East, Sheung Wan, Hong Kong  
Tel.: (852) 2850 8518 Fax: (852) 2850 8515  
Email: paints@taihinghong.biz.com.hk





ISO 9001:2000  
Cert. No. 01 100 6507

### Application Data :

No. of Components : One  
No. of Coats : One~Two  
Dilution : 0 ~ 10% with tap water  
Preceding Coats : No. 410-1 Emulsion Paint, Primer  
Application Method : Spray, Brush, Roller

### 使用說明 :

組合成份數目 : 1  
塗施層面 : 1 ~ 2  
稀釋 : 0 ~ 10% 自來水  
適用底漆 : No.410-1 白色水性水泥底漆  
塗裝方法 : 噴塗, 刷塗, 滾塗

### Packing Style :

No. 410 Rainbow Emulsion Paints  
4.54 Kg/ USG/ Can  
22.71 Kg/ 5USG/ DR

### 包裝 :

No.410 彩虹漆  
4.54 公斤/美卡/ 罐  
22.71 公斤/5美卡/ 桶



### Material Handling :

1. The moisture, grease, dirt, dust and other contaminants on applied surface must be cleaned thoroughly.
2. Before application, stir paint evenly, and when paint is too thick the tap water can be added within specified quantity.
3. Moisture and alkali will reduce film performance and adhesion, therefore, moisture content of new constructed cement walls should be under 12%. If not, the application has to wait for 2 or 3 weeks until the walls is dry completely
4. For spray application the necessary health precautions must be observed.
5. Ensure adequate ventilation during application.
6. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

### 注意事項 :

1. 被塗物表面之油脂, 灰塵, 水份及其他附著物, 必須清除乾淨才能施工
2. 使用前必須充分攪拌, 太稠時, 可酌加自來水調薄, 但以不超過規定量為原則
3. 新水泥牆壁因含有水份與游離鹼性物質, 必將降低漆膜性能與附性, 必須等2~3星期, 待其完全乾燥後, 水份值在12% 以下, 始可施工
4. 噴塗施工時, 必須注意一切安全措施
5. 在施工時保證足夠空氣流通
6. 如稀釋劑非由我們推薦的, 我們將不會保證任何有關使用上所引至的後果及缺點



虹牌油漆

TAI HING HONG 大興行

Main Office:  
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong  
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:  
Unit 1906, 19/F., Bonham Trade Centre,  
50 Bonham Strand East, Sheung Wan, Hong Kong  
Tel.: (852) 2850 8518 Fax: (852) 2850 8515

