



# Synthetic Enamel, Colors

## 鮮麗漆



ISO 9001  
Cert. No. 09 100 6507

### Product No. : 501

### 產品編號 : 501

#### **General Description :**

Glossy topcoat based on alkyd and weather resistant pigments.

#### **一般說明 :**

由油性矽酸酐樹脂為主要成份, 配以耐候性顏料精製而成之鮮麗面漆.

#### **Uses :**

Metal, woodenware, machinery vehicles and steel structure surfaces.

#### **用途 :**

一般鐵材, 木製品, 機械設施, 車輛及鋼鐵構造物等之面塗用漆.

#### **Characteristics :**

1. Very fast drying.
2. Excellent gloss and appearance.
3. Excellent resistance to weathering and gloss retention.
4. Tough film with good abrasion.
5. Excellent oil and heat resistance; can bear with temporary immersion of gasoline and oil.
6. Easy application.

#### **特點 :**

1. 乾燥迅速
2. 塗面平滑, 有良好光澤
3. 具有良好耐候性, 不易失光, 變黃或粉化
4. 漆膜堅韌, 附著力強
5. 耐油性良好, 能承受短暫之機油或汽油之浸漬
6. 容易施工

#### **Color Availability :**

Different color

#### **可調配顏色 :**

各色

**Technical Data :****技術資料 :**

Finish

光澤

Above 85%

85% 以上

Weight

重量

Above 1.0 Kg/ L

1.0 公斤/ 公升 以上

Viscosity (25 °C)

黏度 (25 °C)

70~90 KU

70~90 KU

Hiding Power

遮蓋力

Red and deep color above 6 m<sup>2</sup>/ LBlack color above 20m<sup>2</sup>/L,Other color above 12.5m<sup>2</sup>/L紅色及深色 6m<sup>2</sup>/公升以上黑色 20m<sup>2</sup>/公升以上

其他顏色12.5平方米/公升以上

Drying Time (25 °C)

乾燥時間 (25 °C)

Set-to-touch

1½ hr

指觸

1½ 小時

Dry hard

8 hrs

堅結

8 小時

Optimum Film Thickness

塗膜厚度

Wet

90 microns

濕膜

90 微米

Dry

35 microns

乾膜

35 微米

Non-volatile Content

總不揮發物

Black color Above 45%, other 50%

黑色45% 其他顏色50%以上

Theoretical Coverage

理論塗佈量

Min.

42.0 m<sup>2</sup>/ Gal , 11.0 m<sup>2</sup>/ L , 10.0 m<sup>2</sup>/ Kg

最少

42.0 平方米/ 美卡 , 11.0 平方米/ 公斤

Temperature Resistance

耐熱溫度

Continuous

93 °C

連續

93 度

Intermittent

121 °C

間歇

121 度

Overcoating Intervals

塗裝間隔

Min.

8 hrs

最少

8 小時

Storage Shelf Life

貯存安定性

Minimum 1 year under normal condition

正常情況下, 至少一年



虹牌油漆

TAI HING HONG 大興行

香港仔石排灣道一〇三號地下  
 103, G/F, Shek Pai Wan Road, Aberdeen, Hong Kong.  
 Tel : (852) 2873 3078  
 Fax : (852) 2873 4953  
 E-mail: taihinghong@ctimail.com





## Material Handling :

1. Ensure adequate ventilation during application.
2. All equipments must be cleaned immediately after use.
3. Avoid contact with eyes. Any eye contamination should be washed immediately with plenty of water and seek medical treatment.
4. Before application, stir paint evenly, and when paint is too thick, thinner can be added according to specified quantity.
5. Adhered moisture, grease, dirt, damaged or loose paint film and corrosive salts on substrate must be removed thoroughly.
6. Application must be suspended when substrate is damp with dew, or during rainy weather; or under high temperature (above 40 °C) or low temperature (under 10 °C).
7. For heavy duty chemical resistant applications, two coats of both primer and topcoat must be coated to ensure effective resistance to acids and alkalis.
8. Keep away from heat sources.
9. Store materials in a cool, well-ventilated and dry place, away from direct sunlight.
10. If alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

## 注意事項 :

1. 在施工時保證足夠空氣流通
2. 各項工具於使用完畢, 需立即清洗
3. 避免接觸眼睛, 如不幸發生應立即以清水沖洗和找醫生醫治
4. 使用前必須充分攪拌均勻, 太稠時, 可酌加調薄劑調薄, 但以不超過規定量為原則
5. 被塗物表面之水份. 油脂, 鐵銹, 污泥, 損毀或鬆懈漆膜及腐蝕性鹽類等, 附著污物必須清除乾淨, 以確保油漆之防護功能
6. 表面潮濕凝結有露水或在陰雨天, 以及溫度過高 (40 °C) 或過低 (10 °C 以下時), 應避免施工
7. 做疊層塗裝時, 必須等待下層漆膜完全乾燥後, 始可施工.
8. 遠離熱源
9. 貯存於清涼, 乾爽, 空氣流通地方, 避免陽光直接照射
10. 如稀釋劑非由我們推薦的, 我們將不會保證任何有關使用上所引致的後果及缺點



TAI HING HONG 大興行

香港仔石排灣道一〇三號地下  
103, G/F., Shek Pai Wan Road, Aberdeen, Hong Kong.  
Tel : (852) 2873 3078  
Fax : (852) 2873 4953  
E-mail: taihinghong@ctimail.com

