



Flat Emulsion Paint

平光型水性水泥漆



Product No. : 860

產品編號 : 860

General Description :

The waterborne emulsion paint based on the water and alkali resistance acrylic copolymer with the special pigment and additives.

一般說明 :

由耐水, 耐鹼性非常優異之水性樹脂, 配合遮蓋顏料及添加劑精製而成

Uses :

Topcoat for interior walls of office building, hotel, public place, hospital, store, residence for the purpose of protection and decoration.

用途 :

辦公大樓, 觀光飯店, 公共場所, 醫院, 店舖, 住宅等水泥, 磚造物, 石膏等內部構造物之防護, 裝飾用面漆

Characteristics :

1. Solvent is tap water, no pollution and flaming danger.
2. Thinning with tap water to lower the application expense.
3. Excellent anti-fungi capability.
4. Tough and hard film with smooth appearance.
5. Excellent resistance to moisture and alkalis.
6. Easy application.

特點 :

1. 使用清水為溶劑, 無公害及引火危險
2. 以清水為調薄劑, 可大幅降低施工費用
3. 防霉性極優
4. 具有平光外觀, 塗膜堅固, 外表美觀柔和
5. 耐水性, 耐鹼性優良
6. 容易施工

Color-Availability :

White and desired colors

可調配顏色 :

白色及指定色

Technical Data :Finish
光澤Weight
重量Viscosity (25°C)
黏度 (25°C)Drying Time (25°C)
乾燥時間 (25°C)Optimum Film Thickness
漆膜厚度Overcoating Intervals (25°C)
塗裝間隔 (25°C)Theoretical Coverage
理論塗佈量Storage Shelf Life
貯藏安定性**技術資料:**0-10%
平光above 1.3 Kg/L
1.3公斤/公升以上80 ~ 110KU
80 ~ 110KUSet-to-touch
指觸
Dry hard
硬乾 $\frac{1}{2}$ hr
 $\frac{1}{2}$ 小時
2 hrs
2 小時Wet
濕膜
Dry
乾膜90 microns
90 微米
35 microns
35 微米Min.
最少3 hrs
3 小時42.0 m²/ Gal, 11.1 m²/ L, 8.5 m²/ Kg
42.0 平方米/ 加侖, 11.1 平方米/ 公升
8.5 平方米/ 公斤Minimum 1 year under normal storage conditions
正常情況下, 至少1年

虹牌油漆

TAI HING HONG 大興行

香港仔石排灣道一〇三號地下
103, G/F., Shek Pai Wan Road, Aberdeen, Hong Kong.

Tel : (852) 2873 3078

Fax : (852) 2873 4953

E-mail: taihinghong@ctimail.com





ISO 9001
Cert. No. 09 100 6507

Application Data :

No. of Components : One
No. of Coats : One~Two
Dilution : 10 ~ 20% with tap water
Preceding Coats : No. 410-1 Emulsion Paint, Primer
Application Method : Spray, Brush, Roller

使用說明：

組合成份數目 : 1
塗施層面 : 1~2
稀釋 : 10 ~20% 自來水
適用底漆 : No.410-1白色水性水泥底漆
塗裝方法 : 噴塗, 刷塗, 滾塗

Packing Style :

No. 860 Flat Emulsion Paint
4.92 Kg/USG/Can
24.6 Kg/5USG/DR

包裝：

No.860 平光型水性水泥漆
4.92 公斤/美卡/罐
24.6 公斤/5美卡/桶



Material Handling :

1. The moisture, grease, dirt, dust and other contaminants on applied surface must be cleaned thoroughly.
2. Before application, stir paint evenly, and when paint is too thick the tap water can be added within specified quantity.
3. Moisture and alkali will reduce film performance and adhesion, therefore, moisture content of new constructed cement walls should be under 12%. If not, the application has to wait for 2 or 3 weeks until the walls is dry completely.
4. The Rainbow color toners or emulsion paints are specified for thinning, if required.
5. For spray application the necessary health precautions must be observed.
6. Ensure adequate ventilation during application.
7. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

注意事項:

1. 被塗物表面之油脂, 灰塵, 水份及其他附著物, 必須清除乾淨才能施工
2. 使用前必須充分攪拌, 太稠時, 可酌加自來水調薄, 但以太不超過規定量為原則
3. 新水泥牆壁因含有水份與游離鹼性物質, 必將降低漆膜性能與附著性, 必須等2-3乾燥星期, 待其完全後, 水份值在12% 以下, 始可施工
4. 調色時請用虹牌水性色素
5. 噴塗施工時, 必須注意一切安全措施
6. 在施工時保證足夠空氣流通。
7. 如稀釋劑非由我們推薦的, 我們將不會保證任何有關使用上所引至的後果及缺點



虹牌 油漆

TAI HING HONG 大興行

香港仔石排灣道一〇三號地下
103, G/F., Shek Pai Wan Road, Aberdeen, Hong Kong.

Tel : (852) 2873 3078

Fax : (852) 2873 4953

E-mail: taihinghong@ctimail.com

