



Epoxy Tar, HB

永保新柏油漆, 厚塗型



Product No. : EP-06 (1004)

產品編號: EP-06 (#1004)

General Description :

A two-pack, high build type anti-corrosive paint based on Epoxy/Coal Tar.

一般說明 :

由環氧樹脂及柏油等構成之二液型厚塗防銹漆。

Uses :

Anti-corrosive paint for ballast tanks, cargo oil tanks, cargo hold steel pipes chain lockers and anti-corrosive paint for bridge, chemical plant, water pipe and sewage exhaust pipe etc.

用途 :

船舶, 壓水艙, 貨艙, 油艙及錨鍊以及橋樑, 化學工廠, 水渠地下道, 混凝土管或發電廠, 進排水冷卻鋼管及污水放流鋼管等內部防蝕工程用漆

Characteristics :

1. Tough and hard film.
2. Excellent resistance to sea water, and mechanical damage.
3. High build (250 micron film can be obtained by one coat spray).
4. Very good resistance to galvanic action.
5. Relatively low cost.

特點 :

1. 漆膜堅硬而柔韌
2. 耐海水及耐機械磨損性極優, 可做儲槽內襯用。
3. 噴漆一度可得250微米以上厚漆膜
4. 耐電蝕性極強
5. 價格低廉

Color-Availability :

Black or Brown

可調配顏色 :

黑色及棕色

Technical Data :**技術資料 :**

Finish 光澤		Semi-gloss 半光
Weight 重量		1.3 Kg/ L 1.3 公斤/公升
Viscosity (25 °C) 黏度		80 ~ 100 KU 80 ~ 100 KU
Drying Time (25 °C) 乾燥時間	Set-to-touch 指觸	3 hrs 3 小時
	Dry hard 堅膜	14 hrs 14 小時
	Fully cured 完全硬化	7 days 7 天
Optimum Film Thickness 漆膜厚度	Wet 濕膜	368 microns 368 微米
	Dry 乾膜	250 microns 250 微米
Overcoating Intervals (25 °C) 塗裝間隔 (25°C)	Min. 最少	18 hrs 18 小時
	Max. 最多	5 days 5 天
Theoretical Coverage 理論塗佈量		10.30 m ² / US Gallon , 2.1 m ² / Kg 10.3平方米/美卡, 2.1 平方米/公斤
Solid by Volume 固體容積		68%
		68%
Stock Shelf Life 貯藏安定性		Minimum 1 year under normal storage conditions. 正常情況下, 至少一年



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk





ISO 9001:2000
Cert. No. 01 100 6507

Application Data :

No. of Component(s) : Two
No. of Coat(s) : One~Two
Dilution : 0~5% (by wt.)
SP-12 Epoxy Thinner.
Preceding Coats : SP-01 Blast Primer.
SP-04 Epoxy Zinc Rich Primer.
SP-09 Cathozinc Shop Primer
Type-2.
Application Method : Airless Spray, Brush, Roller.
For Airless Spray : Tip Size : 0.021" ~ 0.027"
: Air Pressure : 5 ~ 6 kg/ cm²
: Pump Ratio : 28 : 1 or Greater

使用說明 :

組合成份數目 : 2
塗施層面 : 1-2
稀釋 : 5~10% (重量比)
SP-12 永保新調薄劑。
適用底漆 : SP-01 長曝型伐銹底漆
SP-04 永保新鋅粉底漆
SP-09 無機鋅粉預塗底漆
塗裝方法 : 無氣噴塗, 刷塗, 滾塗。
無氣噴塗要求 : 噴嘴尺寸: 0.021"~0.027"
二次空氣壓力: 5~6kg/cm²
壓縮比 : 28:1 或更大

Packing Style :

4.92 Kg/ USG /Can
24.6 Kg/ 5USG/ DR

包裝:

4.92 公斤/ 美卡/ 罐
24.6 公斤/ 5美卡/ 桶

Material Handling :

1. For spray application the necessary health precautions must be observed.
2. Keep away from heat sources.
3. Mix base and hardener according to the mixing ratio and stir thoroughly.
4. Avoid applying the paint in rainy or humid weather, particularly, a wet surface must be thoroughly dried.
5. All equipments must be cleaned immediately after use.
6. When used inside tanks, sufficient ventilation must be provided.
7. When overcoating interval is exceeded paint surface must be roughened to insure adhesion.
8. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

注意事項 :

1. 噴塗施工時,必須注意一切安全措施.
2. 遠離熱源.
3. 主劑及硬化劑,必須按規定比例,均勻調合.
4. 陰雨或大氣相對濕度在85% RH 以上時,儘量避免施工,尤以表面潮濕者,必須使之完全乾燥.
5. 各項工具於使用完畢,須立刻洗淨.
6. 於貯槽內施工時,須注意予以充份通風.
7. 被塗物表面之水份,油脂,污泥,灰塵等附著物必須清除乾淨.
8. 如稀釋劑非由我們推薦的,我們將不會保證任何有關使用上所引至的後果及缺點.



虹牌油漆

TAI HING HONG 大興行

Main Office:
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:
Unit 1906, 19/F., Bonham Trade Centre,
50 Bonham Strand East, Sheung Wan, Hong Kong
Tel.: (852) 2850 8518 Fax: (852) 2850 8515
Email: paints@taihinghong.biz.com.hk

