



# Chlor Rubber Finish

## 橡膠面漆



ISO 9001:2000  
Cert. No. 01 100 6507

**Product No. : RF-51~56**

**產品編號 : RF-51~56**

### General Description :

Finish paint based on Chlorinated Rubber and special resins with weather and chemical resistant pigments.

### 一般說明 :

由氯化橡膠 (Chlorinated Rubber) 及特殊合成樹脂為主要原料, 配以耐候, 耐酸, 耐鹼顏料精製而成之橡膠面漆.

### Uses :

Heavy duty topcoat for steel structures of power plants, chemical factories, ships, bridges and tanks etc.

### 用途 :

船舶, 曝露大氣環境或橋樑, 貯槽外露面, 發電廠及化學工廠, 煉油廠等之鋼鐵構造物與設施防蝕用面漆.

### Characteristics :

1. Very fast drying with very good adhesion.
2. Very good resistance to weathering.
3. Very good resistance to sea water.
4. Good resistance to oils, acids and alkalis.
5. Good resistance to mechanical damage.

### 特點 :

1. 乾燥極速, 附着力極優.
2. 耐候性極優.
3. 耐海水性極優.
4. 耐酸, 耐鹼, 耐油等耐化學品性能特優.
5. 耐機械磨損性優良.

### Color-Availability :

White and desired colors

### 可調配顏色 :

白色及指定色

**Technical Data :**

Finish

光澤

Weight

重量

Viscosity (25 °C)

黏度 (25 °C)

Drying Time (25 °C)

乾燥時間 (25 °C)

Optimum Film Thickness

漆膜厚度

Overcoating Intervals (25°C)

塗料間隔 (25°C)

Theoretical Coverage

理論塗佈量

Solid by Volume

固體容積

Stock Shelf Life

貯藏安定性

**技術資料:**

Semi-glass

半光

1.2 Kg/L (depending on colors)

1.2 公斤/公升 (因色而異)

70 ~ 85 KU

70 ~ 85 KU

Set-to-touch

1/2 hr

指觸

1/2 小時

Dry hard

3 hrs

堅膜

3 小時

Wet

85 microns (3.4 mil)

濕膜

85 微米 (3.4 mil)

Dry

35 microns (1.4 mil)

乾膜

35 微米 (1.4 mil)

Min.

4 hrs

最少

4 小時

11.8 m<sup>2</sup>/L, 9.8 m<sup>2</sup>/Kg

11.8 平方米/公升, 9.8 平方米/公斤

41%

41%

Minimum 1 year under normal storage conditions

正常情況下, 至少1年

**TAI HING HONG 大興行**

Main Office:  
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong  
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:  
Unit 1906, 19/F., Bonham Trade Centre,  
50 Bonham Strand East, Sheung Wan, Hong Kong  
Tel.: (852) 2850 8518 Fax: (852) 2850 8515  
Email: paints@taihinghong.biz.com.hk

**虹牌油漆**



ISO 9001:2000  
Cert. No. 01 100 6507

### Application Data :

No. of Component(s) : One  
 No. of Coat(s) : One~Two  
 Dilution : 0~5% (by wt.) RP-71 PCR Thinner  
 Preceding Coats : RP-61 CR Primer, High Red Lead  
 RP-64 CR Primer, LZI  
 RP-64-1 CR Primer, LZI, HB  
 RP-65 CR Primer, Red Oxide  
 RP-67 CR Primer, Zinc Chromate

Application Method : Airless Spray, Brush, Roller

For Airless Spray : Tip Size : 0.017" ~ 0.019"  
 : Air Pressure : 5 ~ 6 kg/cm<sup>2</sup>  
 : Pump Ratio : 23 : 1 or Greater

### 使用說明 :

組合成份數目 : 1

塗施層面 : 1~2

稀釋 : 0~5% (重量比)  
 RP-71 橡膠調薄劑

適用底漆 : RP-61 橡膠船用紅丹漆.  
 RP-64 橡膠鋅鉻鐵鉛底漆.  
 RP-64-1 橡膠鋅鉻鐵鉛底漆,厚塗.  
 RP-65 橡膠鎳色防銹底漆.  
 RP-67 橡膠鋅鉻黃底漆.

塗裝方法 : 無氣噴塗, 刷塗, 滾塗

無氣噴塗要求 : 噴嘴尺寸 : 0.017"~0.019"  
 二次空氣壓力 : 5 ~ 6 kg/cm<sup>2</sup>  
 壓縮比 : 23 : 1 或更大

### Packing Style :

RF-51~56 Chlor Rubber Finish 4.6 Kg /USG /Can  
 23 Kg /5USG /DR

### 包裝 :

RF-51~56 橡膠面漆 4.6 公斤/美卡/罐  
 23 公斤/ 5美卡/桶

## Material Handling :

1. For spray application the necessary health precautions must be observed.
2. Keep away from heat sources.
3. When substrate is damp with dew or during rainy weather painting must be suspended.
4. Adhered moisture, grease, dirt damaged or loose old paint and corrosive salts on substrate must be cleaned thoroughly.
5. All equipments must be cleaned immediately after use.
6. When used inside tanks, sufficient ventilation must be provided.
7. Before application stir paint evenly, and when paint is too thick, CR thinner within specified quantity can be added.
8. For heavy duty chemical resistant applications, two coats of both primer and topcoat must be coated to insure effective resistance to acids and alkalis.
9. If an alternative thinner is used for dilution other than our recommended thinner we will not be liable for any complications or defects arising from the usage of this material.

## 注意事項 :

1. 噴塗施工時,必須注意一切安全措施.
2. 遠離熱源.
3. 表面潮濕,凝結有露水或在陰雨天時,應避免施工.
4. 被塗物表面水份,油脂,污泥,灰塵,損毀或鬆懈舊漆膜及腐蝕性鹽類等附著污物必須清除乾淨.
5. 各項工具於使用完畢,須立刻洗淨.
6. 於貯槽內施工時,須注意予以充份通風.
7. 使用前必須充分攪拌均勻.油漆如太稠時,可酌加橡膠調薄劑調薄,但以不超過規定量為原則.
8. 做耐酸,云鹼防蝕塗裝時,必須做底,面漆各二次以上確保防酸,鹼功能.
9. 如稀釋劑非由我們推薦的,我們將不會保證任何有關使用上所引至的後果及缺點.



No. RP-51~56

虹牌油漆

## TAI HING HONG 大興行

Main Office:  
G/F., 103 Shek Pai Wan Road, Aberdeen, Hong Kong  
Tel.: (852) 2873 3078 Fax: (852) 2873 4953

Sheung Wan Office:  
Unit 1906, 19/F., Bonham Trade Centre,  
50 Bonham Strand East, Sheung Wan, Hong Kong  
Tel.: (852) 2850 8518 Fax: (852) 2850 8515  
Email: paints@taihinghong.biz.com.hk

